

RECEIVED
CENTRAL FAX CENTER

SEP 16 2004

Aromatic High-Strength Fibers

H. H. YANG
Fibers Department
E. I. du Pont de Nemours & Co., Inc.
Richmond, Virginia



WILEY

A WILEY-INTERSCIENCE PUBLICATION

JOHN WILEY & SONS

New York • Chichester • Brisbane • Toronto • Singapore

Table II-25. Typical Properties of Kevlar Aramid Yarn^a

Denier	1500
Number of filaments	1000
Specific gravity	1.44
Moisture regain (commercial) (%)	7.0
Stress-strain properties	
Straight tests on conditioned yarn	
Breaking strength (lb)	73.0
Breaking tenacity (gpd)	22.0
Elongation at break (%)	4.0
Initial modulus (gpd)	475
Loop tests on conditioned yarn	
Breaking strength (lb)	70.0
Breaking tenacity (gpd)	10.5
Elongation at break (%)	2.3
Thermal properties	
Strength loss (% after 48 h) in dry air at 350°F (180°C)	16
Shrinkage (%) in dry air at 320°F (160°C)	0.2
Zero-strength temperature, °F (°C)	850(455)
Half-strength temperature, °F (°C)	750(400)
Specific heat (cal/g°C at 25°C)	0.4
Thermal conductivity (Btu/hr/ft ² /°F/in. of thickness)	0.3

^a From Du Pont (76).

and other tire yarns. Table II-28 compares the tensile properties of Kevlar 49 and several industrial filament yarns. Overall, Kevlar is an outstanding high-strength, high-modulus fiber. Its tenacity (strength per linear density unit) is greater than all conventional fibers. Its strength is relatively insensitive to temperatures up to T_g , and it is dimensionally stable. These features are discussed in the following sections.

7.3.1. Color

Most Kevlar fiber products have a bright yellow color. Some product types, for example, Kevlar 49, have a deep gold color.

7.3.2. Fiber Denier and Diameter

Most Kevlar fibers are 1.5 denier/filament (1.7 dtex). These fibers have a round cross-section and a nominal diameter of 0.012 mm. Fibers of 2250-denier Kevlar and 2130-denier Kevlar 49 yarns have a fineness of 2.25 denier (2.50 dtex) and 0.0147-mm nominal diameter.

Copyright © 1989 by John Wiley & Sons, Inc.

All rights reserved. Published simultaneously in Canada.

Reproduction or translation of any part of this work beyond that permitted by Section 107 or 108 of the 1976 United States Copyright Act without the permission of the copyright owner is unlawful. Requests for permission or further information should be addressed to the Permissions Department, John Wiley & Sons, Inc.

Library of Congress Cataloging-in-Publication Data

Yang, H. H.

Aromatic high strength fibers/H. H. Yang.

p. cm.—(SPE monographs, ISSN 0195-4283)

"A Wiley-Interscience publication."

Bibliography: p.

Includes index.

ISBN 0-471-62988-X

1. Textile Fibers, Synthetic—Congresses. 2. Aromatic compounds—
—Congresses. I. Title. II. Title: High strength fibers.

III. Series.

T51.S48.Y36 1989

677'.4—dc20

88-28190

CIP

Printed in the United States of America

10 9 8 7 6 5 4 3 2 1